

AD-A092 821

FOREIGN TECHNOLOGY DIV WRIGHT-PATTERSON AFB OH

F/G 7/4

TWO-PHOTON ABSORPTION IN CRYSTALS WITH THE PRESENCE OF ELECTRIC--ETC(U)

NOV 80 S K S'YNOV

UNCLASSIFIED

FTD-ID(R5)T-1523-80

NL

For I  
AD-A  
092821



0								
END								
DATE								
FILMED								
-8-								
DTIC								

2

FOREIGN TECHNOLOGY DIVISION




TWO-PHOTON ABSORPTION IN CRYSTALS WITH THE PRESENCE  
OF ELECTRIC FIELD

by

S. Kh. S"ynov

DTIC  
ELECTE  
DEC 12 1980  
S D E



Approved for public release;  
distribution unlimited.

AD A092821

DDC FILE COPY

80 12 11 092

## EDITED TRANSLATION

(14)

FTD-ID(RS)T-1523-80

(11) 14 Nov 80 /

14 November 1980

MICROFICHE NR: FTD-80-C-001123

(6)

TWO-PHOTON ABSORPTION IN CRYSTALS WITH THE  
PRESENCE OF ELECTRIC FIELD,

(12) 8 /

By (10) S. Kh. / S. Ynov

English pages: 5

(21) Edited trans. of

Source: Doklady Bolgarskoy Akademii Nauk,  
Vol. 25, Nr. 3, 1972, pp. 301-303

Country of origin: (USSR) Vol 25 Nr 3 p 301-303 1972, by

Translated by: Robert Allen Potts

Requester: FTD/TQTD

Approved for public release; distribution  
unlimited.

THIS TRANSLATION IS A RENDITION OF THE ORIGINAL FOREIGN TEXT WITHOUT ANY ANALYTICAL OR EDITORIAL COMMENT. STATEMENTS OR THEORIES ADVOCATED OR IMPLIED ARE THOSE OF THE SOURCE AND DO NOT NECESSARILY REFLECT THE POSITION OR OPINION OF THE FOREIGN TECHNOLOGY DIVISION.

PREPARED BY:

TRANSLATION DIVISION  
FOREIGN TECHNOLOGY DIVISION  
WP-AFB, OHIO.

FTD -ID(RS)T-1523-80

Date 14 Nov 1980

24-14000 alk

# U. S. BOARD ON GEOGRAPHIC NAMES TRANSLITERATION SYSTEM

Block	Italic	Transliteration	Block	Italic	Transliteration
А а	<i>А а</i>	A, a	Р р	<i>Р р</i>	R, r
Б б	<i>Б б</i>	B, b	С с	<i>С с</i>	S, s
В в	<i>В в</i>	V, v	Т т	<i>Т т</i>	T, t
Г г	<i>Г г</i>	G, g	У у	<i>У у</i>	U, u
Д д	<i>Д д</i>	D, d	Ф ф	<i>Ф ф</i>	F, f
Е е	<i>Е е</i>	Ye, ye; E, e*	Х х	<i>Х х</i>	Kh, kh
Ж ж	<i>Ж ж</i>	Zh, zh	Ц ц	<i>Ц ц</i>	Ts, ts
З з	<i>З з</i>	Z, z	Ч ч	<i>Ч ч</i>	Ch, ch
И и	<i>И и</i>	I, i	Ш ш	<i>Ш ш</i>	Sh, sh
Й й	<i>Й й</i>	Y, y	Щ щ	<i>Щ щ</i>	Shch, shch
К к	<i>К к</i>	K, k	Ъ ъ	<i>Ъ ъ</i>	"
Л л	<i>Л л</i>	L, l	Ы ы	<i>Ы ы</i>	Y, y
М м	<i>М м</i>	M, m	Ь ь	<i>Ь ь</i>	'
Н н	<i>Н н</i>	N, n	Э э	<i>Э э</i>	E, e
О о	<i>О о</i>	O, o	Ю ю	<i>Ю ю</i>	Yu, yu
П п	<i>П п</i>	P, p	Я я	<i>Я я</i>	Ya, ya

\*ye initially, after vowels, and after Ъ, ь; e elsewhere.  
When written as ë in Russian, transliterate as yë or ë.

## RUSSIAN AND ENGLISH TRIGONOMETRIC FUNCTIONS

Russian	English	Russian	English	Russian	English
sin	sin	sh	sinh	arc sh	sinh
cos	cos	ch	cosh	arc ch	cosh
tg	tan	th	tanh	arc th	tanh
ctg	cot	cth	coth	arc cth	coth
sec	sec	sch	sech	arc sch	sech
cosec	csc	csch	csch	arc csch	csch

Russian	English
rot	curl
lg	log

1523

## TWO-PHOTON ABSORPTION IN CRYSTALS WITH THE PRESENCE OF ELECTRIC FIELD

S. Kh. S"ynov.

Submitted by corres. member M. Borisovyy 23 Sept. 1971.

Accession For	
NTIS GRL&I	
DDC TAB	
Unannounced	
Justification	
By _____	
Distribution/	
Availability Codes	
Dist.	Avail and/or special
A	

The theory of two-photon absorption was developed by Goppert-Mayer. It was applied to a solid by Braunstein [2] and Loudon [3]. According to [2] the probability of the fact that an electron from a valence zone simultaneously absorbs two noncoherent photons:  $\hbar\omega_1$  and  $\hbar\omega_2$  and converts into a zone of conductivity is expressed:

$$W = \frac{8\pi^2 \hbar e^4 N_1 N_2}{m^4 \omega_1 \omega_2} \int \frac{d^3 k}{(2\pi)^3} \left[ \frac{|p_{vn}^{(1)}|^2 |p_{nc}^{(2)}|^2}{(E_{nk} - E_{vk} - \hbar\omega_1)^2} + \frac{|p_{vn}^{(2)}|^2 |p_{nc}^{(1)}|^2}{(E_{nk} - E_{vk} - \hbar\omega_2)^2} \right] \cdot \delta(E_{ck} - E_{vk} - \hbar\omega_1 - \hbar\omega_2) \quad (1)$$

For case "allowed"-"allowed" transition the matrix element of the moment is written (4).

(2)

$$P_{ij} = H_{ij}(\vec{k}_0) \Phi(0) \delta(\vec{k})$$

where  $H_{ij}$  matrix elements, computed with the aid of periodic parts of Bloch functions between corresponding states. In this case they are constants.  $\Phi(\vec{r})$  is the solution of Shrodinger equation for electron-hole pair in the presence of electric field  $\vec{F}$ , if we disregard the Coulomb interaction between them

$$(3) \quad \left[ (a_i + a_f) \frac{\vec{p}^2}{2m} + e\vec{F} \cdot \vec{r} \right] \cdot \Phi(\vec{r}) = E_i \Phi(\vec{r})$$

$a_{i,f}$  is the relationship between the mass of free electron and the effective mass in the corresponding zone. Equation (3) is solved in [5] and is used during computation of the coefficient of electric absorption by K. Tharmalingam [6]. According to [4] in cylindrical coordinates

$$(4) \quad E_i = E_z + \frac{\hbar^2 k_z^2}{2m} (a_i + a_f)$$

$$(5) \quad \Phi_i(\vec{r}) = \beta_{if} \frac{1}{2\pi\hbar} \exp(ik_z z) \cdot A_i \left( \frac{-E_z - eF_z}{\gamma_{if}} \right)$$

$$(6) \quad \beta_{if} = \frac{\left( \frac{2m}{a_i + a_f} \right)^{\frac{1}{3}}}{\pi^{\frac{1}{2}} (eF)^{\frac{1}{6}} \hbar^{\frac{2}{3}}}$$

$$(7) \quad \gamma_{if} = \left[ \frac{(a_i + a_f)\hbar^2}{2m} \right]^{\frac{1}{3}} (eF)^{\frac{2}{3}}$$

$E_z$  depending on the electric field of energy.  $A_i(x)$  Airy function.

For a model with three levels

$$\begin{aligned}
 E_{vh} &= -a_v \frac{\hbar^2 k^2}{2m} \\
 E_{ch} &= E_g + a_c \frac{\hbar^2 k^2}{2m} + E_z \\
 E_{nh} &= \Delta E + a_n \frac{\hbar^2 k^2}{2m} + E_z
 \end{aligned}
 \quad (8)$$

The absorption coefficient for photon  $\hbar\omega_1$  is expressed:

$$K_1 = \frac{2\pi}{c} \frac{W}{N_1} \quad (9)$$

After substitution of  $W$  from (1) and from (2), (5) and (8) we obtain the following expression for  $K_1$ , introducing the density of states:

$$\begin{aligned}
 (10) \quad K_1 &= \frac{2\pi n e^4 N_g^2 \beta_{nc}^2 \beta_{vn}^2 H_{nc}^2 H_{vn}^2}{c m^3 \hbar \omega_1 \omega_2 (a_c + a_v) (2\pi \hbar)^4} \int_0^\infty \int_{-\infty}^\infty \frac{A_i^2 \left( -\frac{E_z}{\gamma_{nc}} \right) \cdot A_i^2 \left( -\frac{E_z}{\gamma_{vn}} \right)}{\left( \Delta E + \frac{a_n + a_v}{2m} \hbar^2 k^2 + E_z - \hbar\omega_1 \right)} + \\
 &+ \frac{A_i^2 \left( -\frac{E_z}{\gamma_{nc}} \right) \cdot A_i^2 \left( -\frac{E_z}{\gamma_{vn}} \right)}{\left( \Delta E + \frac{a_n + a_v}{2m} \hbar^2 k^2 + E_z - \hbar\omega_2 \right)} \Bigg] k_0 dk_0 dE_z \delta \left( E_g + \frac{a_c + a_v}{2m} \hbar^2 k_0^2 + E_z - \hbar\omega_1 - \hbar\omega_2 \right)
 \end{aligned}$$

The absorption threshold is expressed so:

$$(11) \quad \hbar\omega_1 + \hbar\omega_2 = E_g + E_z + \frac{a_c + a_v}{2m} \hbar^2 k_0^2$$

Having integrated in terms of  $E_z$  and set

$$\begin{aligned}
 & Eg + \frac{a_c + a_v}{2m} \hbar^2 k_0^2 - \hbar\omega_1 - \hbar\omega_2 = \gamma_{nc} t \\
 (12) \quad & \Delta E + \frac{a_n + a_v}{a_c + a_v} (\hbar\omega_1 + \hbar\omega_2 - Eg) - \hbar\omega_{1,2} = B_{1,2} \\
 & \frac{\gamma_{nc}}{\gamma_{vn}} = \left( \frac{a_c + a_n}{a_c + a_v} \right)^{\frac{1}{3}} = \gamma \\
 & \gamma_{nc} \left( \frac{a_n - a_c}{a_c + a_v} \right) = cp_0
 \end{aligned}$$

With the aid of (6) and (7) we obtain the following expression for  $K_1$

$$\begin{aligned}
 (13) \quad K_1 = & \frac{2^6 n e^4 N_s \hbar^2 H_{nr}^2 H_{vn}^2}{(2\pi \hbar)^3 m c \hbar^3 (a_c + a_n)^{\frac{1}{3}} (a_n + a_v)^{\frac{2}{3}} (a_c + a_v)^2 \omega_1 \omega_2} \\
 & \int_{\frac{E_g - \hbar\omega_1 - \hbar\omega_2}{\gamma_{nc}}}^{\infty} \left[ \frac{1}{(B_1 + pt)^2} + \frac{1}{(B_2 + pt)^2} \right] A_i^2(t) A_i^2(pt) dt
 \end{aligned}$$

As seen from (13) the absorption coefficient  $K_1$  will depend not only on the number of photons  $\hbar\omega_2 = N_s$ , but on the magnitude of the electric field, applied to the crystal. Thanks to this, the absorption can be started with total energy of both photons less than the width of the forbidden zone, similar to single-photon electric absorption. For case

$$a_n = a_v(p=0) \quad \text{and} \quad \hbar\omega_1 + \hbar\omega_2 < E_g$$

we can use the asymptotic formula of Airy function [5]. Let us substitute it in (3) and obtain



$$\begin{aligned}
 (14) \quad K_1 = & \frac{n e^5 F N_2 H_{ec}^2 H_{ec}^2}{(2\pi\hbar)^4 \hbar^2 m^2 c \omega_1 \omega_2 a_c - \frac{1}{6} (a_c + a_v)^3} \times \\
 & \times \left[ \frac{1}{(\Delta E - E_g + \hbar\omega_1)^2} + \frac{1}{(\Delta E - E_g + \hbar\omega_2)^2} \right] \cdot \frac{\exp \left[ -\frac{4}{3} \left( \frac{E_g - \hbar\omega_1 - \hbar\omega_2}{\gamma_{ec}} \right) \left( 1 + \gamma^{\frac{3}{2}} \right) \right]}{\gamma^{\frac{1}{2}} \left( 1 + \gamma^{\frac{3}{2}} \right) (E_g - \hbar\omega_1 - \hbar\omega_2)^{\frac{3}{2}}}
 \end{aligned}$$

Similar to single-photon electric absorption (6) and in this case the absorption coefficient depends exponentially on the energy of photons. \*

FOOTNOTE \* After this work was sent to press, there became known the work of E. Yang. Opt. Communications. 3, 1971, 6, 421, in which there is examined the problem of two-photon transitions in an electric field and the result is expressed with the aid of Airy function.

ENDFOOTNOTE.

#### REFERENCES

- <sup>1</sup>M. Goppert-Mayer. Ann. Phys. 9, 1931, 273, Paris. <sup>2</sup>R. Braunstein, Phys. Rev. 125, 1962, 475; R. Braunstein, N. Ockman. Ibid. 134, 1964, A499. <sup>3</sup>R. Loudon. Proc. Phys. Soc. London, 80, 1962, 952. <sup>4</sup>Е. Джонсон. Сб. "Оптические свойства полупроводников". Изд. Мир, М., 1970. <sup>5</sup>Л. Ландау, Е. Лифшиц. Квантовая механика. ГИФМЛ, М., 1963. <sup>6</sup>K. Tharmalingam, Phys. Rev. 130, 1963, 2204.